



ARDEX WPM 422

Crystalline Waterproofing Admix

Not a vapour barrier - allows concrete to breathe

Permanent: Added to the concrete at time of batching and therefore is not subject to climatic restraints



ARDEX Singapore Pte Ltd
26 Tuas Ave 4
Singapore 639376
Ph: +65 6861 7700
Fax: +65 6862 3381
Email: sales@ardex.com.sg
Website: www.ardex.com.sg

ARDEX WPM 422

Crystalline Waterproofing Admix

DESCRIPTION

ARDEX WPM 422 is added to the concrete mix at the time of batching. ARDEX WPM 422 consists of Portland cement, very fine treated silica sand and various active, proprietary chemicals. These active chemicals react with the moisture in fresh concrete and the by-products of cement hydration to cause a catalytic reaction, which generates a non-soluble crystalline formation throughout the pores and capillary tracts of the concrete.

Thus the concrete becomes permanently sealed against the penetration of water or liquids from any direction. The concrete is also protected from deterioration due to harsh environment conditions.

FEATURES / BENEFITS

Resistant to extreme hydrostatic pressure from either positive or negative surface of the concrete slab

Becomes an integral part of the substrate

Highly resistant to aggressive chemicals

Allow concrete to breathe

Non-toxic

Less costly to apply than most other methods

Permanent; Added to the concrete at time of batching and therefore is not subject to climatic restraints

Increases flexibility in construction scheduling

APPLICATION RANGE

- Residential, commercial application for floors & walls
- Swimming Pool, Reservoirs, Sewage and water treatment plants
- Tunnels and Subway Systems
- Underground Vaults
- Foundations
- Parking Structures

SUBSTRATES

- Pre-Cast Components

BASIC APPLICATION INSTRUCTION

SURFACE PREPARATION

Remove remaining concrete fins and projections, general surface dirt, grease, oil and other contaminants.

DOSAGE AND MIXING

Recommend dosage of ARDEX WPM 422 is 0.8% to 1.5% by weight of cement.

Mixing ratio

The concrete mixes, water mixing and aggregate sizes should be according to the requirements of construction design, a small practice is to be evaluated for each project before big scale uses.

APPLICATION

Prepare the dilution right before applying. Ratio of cement/sand/aggregate of concrete should be remained unchanged. Cement for waterproofing must be fresh, free of lumps. Do not change the original applying methods and tools.

Note: It is important to obtain a homogeneous mixture of ARDEX WPM 422 with concrete. Therefore do not add dry ARDEX WPM 422 directly to wet concrete as this may cause clumping and through dispersion will not occur.

Clean up the tools with water before the compound dries

PRODUCT LIMITATION

Trial mixes should be carried out under project conditions to determine setting time and strength of the concrete.

ARDEX WPM 422 must be stored dry at a minimum temperature of 7°C.

When incorporating ARDEX WPM 422, the temperature of the concrete mix should be above 5°C.

PACKAGING

ARDEX WPM 422 is packed in pail - net weight 20kg.

STORAGE

ARDEX WPM 422 should be stored in the original unopened packaging in cool and dry warehouse at 25°C and 50% relative humidity. When stored under the correct conditions ARDEX WPM 422 will have a shelf life of 12 months.

PRECAUTIONS

ARDEX WPM 422 is non-toxic. However, the content should not be swallowed or inhaled. Care should be taken at all times to avoid contact with eye, mouth, skin. Wear face mask to prevent dust inhalation. In the event of eye contact, wash immediately with water and seek medical treatment.

TECHNICAL DATA

Product Properties

Appearance:	Grey Powder
Bulk density:	Approx. 1.05 - 1.10 kg/litre
Working temperature:	5 - 38°C

Testing Method

Depth of Penetration (DIN 1048)	<15mm
Compressive Strength (ASTM C109)	>40N/mm ²

DISCLAIMER:

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for user's consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

Malaysia:
ARDEX MANUFACTURING SDN BHD (669180-X)
No. 19-1, Jalan Puteri 2/2, Bandur Puteri,
47100, Puchong, Selangor Darul Ehsan
Tel: +60 38060 1139 Fax: +60 38060 0719
Email: sales@ardex.com.sg

Thailand:
ARDEX (THAILAND) CO., LTD
969 2nd Floor Moo, 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540 Thailand
Tel: +66 2316 3069 Fax: +66 2316 3075
Email: sales@ardex.co.th

Vietnam:
Mobile: +84 901 351 308
Email: sales@ardex.com.sg
Malaysia

March 2016